

Braided hose

## FITCOFLEX®-I-PA35

Mechanical, self-extinguishing braided hose made of Polyamide 6.6 with high expansion rate.

### Application:

Bundeling and mechanical, thermal and chemical protection of cable harnesses, sleeves and pipes.

### Operating temperature:

-55°C up to +125°C

### Standard color:

black

Description	Recommend range of application [mm]	
	(Ø min)	(Ø max)
FITCOFLEX-I-PA35 4	3	8
FITCOFLEX-I-PA35 5	4	10
FITCOFLEX-I-PA35 10	8	14
FITCOFLEX-I-PA35 12	10	16
FITCOFLEX-I-PA35 14	10	22
FITCOFLEX-I-PA35 16	14	24
FITCOFLEX-I-PA35 20	18	25
FITCOFLEX-I-PA35 24	21	32
FITCOFLEX-I-PA35 30	28	40
FITCOFLEX-I-PA35 35	30	52
FITCOFLEX-I-PA35 45	38	60
FITCOFLEX-I-PA35 50	35	80
FITCOFLEX-I-PA35 70	45	87

Other sizes on request

### Properties:

- Monofil: Ø 0,25mm from polyamide 6.6
- Self-extinguishing (DIN 75200 / FMVSS 302)
- Excellent mechanical protection
- Fire class (DIN5510 part 1+2)
- Very good fluid resistance
- 100% recycleable
- Low weight, high flexibility

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · [info@gremco.de](mailto:info@gremco.de) · [www.gremco.de](http://www.gremco.de) •

PDS No.: 20240919225600

Version: UWM0924-0

Print Date: 19 Sep. 24

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Braided hose

## FITCOFLEX®-I-PA35

### Packaging options:

On spool, Laser cut lengths in boxes

### Features:

	Testing	Value
Abrasion resistance	LV 312-3 (ISO 6722) PSA 9645870999E GME 8618 D 44 1959	≥ 15000 cycles (class F) ≥ 7000 cycles (class 4) 144000 strokes 144000 strokes
Flammability	FMVSS 302 (DIN 75200)  UL94 V	Self-extinguishing (category B) Flammability class S4  Class V2
Shrinking	ISO 6722	≤ 4%
Impact performance	PSA D421245 LV 312-3	No damages (C/200/50/-30°C) No damages (700/1200g at -40°C)
Smoke-gas toxicity	NF F 16-101 NF F 16-102/STM-S-001  DIN EN 45545-2 (NF X 70-100)	F2  Fulfilled (Requirement R22-> Hazard Level HL3 Requirement R23-> Hazard Level HL3)
Oxygen index	NF F 16-101/NF F 16-102/STM-S-001  DIN EN 45545-2 (EN ISO 5659-2)	I3  Fulfilled (Requirement R22-> Hazard Level HL2 Requirement R23-> Hazard Level HL2)
Hydrolysis resistance	GME 00053	Fulfilled
Thermal ageing	LV312-2	Fulfilled (240 h at 150°C / 3000 h at 125°C)
Hot water jet testing	LV312-3	Fulfilled (No cracks or damages)
Fogging	VW 50180	Fulfilled (≤ 2mg)
Emission	VW 50180	Fulfilled (≤ 50µg C/G)
Smoke density	DIN EN 45545-2 (EN ISO 4589-2)	Fulfilled (Requirement R22-> Hazard Level HL2 Requirement R23-> Hazard Level HL3)