

Braided Hose

FITCOFLEX®-I-PET12

FITCOFLEX®-I-PET12 is a halogen free and self-extinguishing braided hose made of 0,22mm polyester monofilament. It provides an extraordinary high expansion rate as well as a high temperature resistance and excellent mechanical protection.

FITCOFLEX®-I-PET12 is especially suitable for cable and pipe bundling for applications in the automotive industry.

Operating temperature: -55°C to +150°C

Standard color: Black



Bestellbezeichnung	Field of application (mm)	
	(Ø min)	(Ø max)
FITCOFLEX®-I-PET12 3	2	7
FITCOFLEX®-I-PET12 5	3	8
FITCOFLEX®-I-PET12 6	4	8
FITCOFLEX®-I-PET12 8	6	10
FITCOFLEX®-I-PET12 10	8	14
FITCOFLEX®-I-PET12 12	10	19
FITCOFLEX®-I-PET12 13	12	15
FITCOFLEX®-I-PET12 14	12	16
FITCOFLEX®-I-PET12 16	14	22
FITCOFLEX®-I-PET12 20	12	25
FITCOFLEX®-I-PET12 22	20	35
FITCOFLEX®-I-PET12 24	22	35
FITCOFLEX®-I-PET12 26	24	40
FITCOFLEX®-I-PET12 30	28	40
FITCOFLEX®-I-PET12 40	38	50
FITCOFLEX®-I-PET12 50	48	55

Special sizes on request

Key Benefits:

- Melting point 250°C - 260°C
- Self-extinguishing (DIN75200 / FMVSS 302)
- Fire class (DIN5510 part 1+2)
- High expansion & 100% recyclable
- UL94-V2 & very good media resistance

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · www.gremco.de •

PDS No.: 20240426094136

Version: UWM0424-0

Print Date: 10. Mrz. 2025

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Braided Hose

FITCOFLEX®-I-PET12

Packaging: On spools, cut lengths or printed tubing on request.

Properties	Test Method	Typical Value
Mechanical		
Abrasion resistance	LV 312-3 (ISO 6722) PSA 9645870999E GME 8618	≥5,000 cycles (class E) ≥7,000 cycles (class 4) 144,000 strokes
Shrinkage performance	ISO 6722	≤4%
Impact resistance	PSA D421245 LV 312-3	No damage (C/200/50/-30°C) No damage (700/1200g / -40°C)
Thermal		
Long term aging (3.000h x 150°C)	LV312-2	Pass
Short term aging (240h x 175°C)	LV312-2	Pass
Hot water jet test	LV312-3	Pass (No cracks or damage)
Flammability	FMVSS 302 (DIN 75200) DIN 5510-2 Fire test UL94 V	Self-extinguishing (Category B) Flammability class S4 Smoke emission SR2 Dripability class ST2 Classification: V2
Smoke index	NF F 16-101 NF F 16-102/STM-S-001 DIN EN 45545-2 (NF X 70-100)	F2 Pass (Requirement R22 & R23 -> Hazard Level HL3)
Smoke density	DIN EN 45545-2 (EN ISO 4589-2)	Pass (Requirement R22 & R23 -> Hazard Level HL3)
Hydrolysis resistance	GME 00053	Pass
Chemical		
Oxygen index	NF F 16-101 NF F 16-102/STM-S-001 DIN EN 45545-2 (EN ISO 5659-2)	I2 (Requirement R22 & R23 -> Hazard Level HL3)
Fogging	VW 50180	Pass (≤2mg)
Emission	VW 50180	Pass (≤50µg C/G)