

Flexible flame retardant polyolefin heat shrink tubing

## FITCOTUBE® FT-SNV-U(1)

Polyolefin heat shrinkable tube for high-voltage copper busbars of electric vehicles, with a rated voltage of DC60V-1000V or AC25V-660V. Excellent high temperature resistance, elastic recovery, anti-cracking and no visible air bubble trapped after shrinkage.

<b>Operating temperature:</b>	-55°C to +125°C
<b>Shrink temperature:</b>	125°C
<b>Shrink ratio:</b>	2:1, 2.5:1 and 3:1
<b>Standard color:</b>	Black, Orange, Red
<b>Approvals:</b>	According to UL

Description	As supplied(mm)		After recovered (mm)		Applicable rectangular busbar(mm)		Applicable round busbar(mm)	
	Inner diameter (min.)	Wall thickness (nom.)	Inner diameter (max.)	Wall thickness (nom.)				
<b>2:1</b>								
FITCOTUBE® FT-SNV-U(1) 12/6	12.0	0.70 ±0.20	6.0	1.40 ±0.20	≥12	≤15.5	≥7.5	≤10
FITCOTUBE® FT-SNV-U(1) 15/7.5	15.0	0.70 ±0.20	7.5	1.40 ±0.20	≥15	≤18.5	≥9.5	≤12
FITCOTUBE® FT-SNV-U(1) 18/9	18.0	0.70 ±0.20	9.0	1.40 ±0.20	≥18	≤22	≥10.5	≤14
FITCOTUBE® FT-SNV-U(1) 20/10	20.0	0.70 ±0.20	10.0	1.45 ±0.20	≥19	≤25	≥13	≤16
FITCOTUBE® FT-SNV-U(1) 22/11	22.0	0.70 ±0.20	11.0	1.45 ±0.20	≥22	≤28	≥14	≤18
FITCOTUBE® FT-SNV-U(1) 25/12.5	25.0	0.70 ±0.20	12.5	1.50 ±0.20	≥26	≤31	≥16	≤20
FITCOTUBE® FT-SNV-U(1) 28/14	28.0	0.70 ±0.20	14.0	1.50 ±0.20	≥28	≤35	≥18	≤22
FITCOTUBE® FT-SNV-U(1) 30/15	30.0	0.70 ±0.20	15.0	1.50 ±0.20	≥30	≤37.5	≥20	≤24
FITCOTUBE® FT-SNV-U(1) 35/17.5	35.0	0.70 ±0.20	17.5	1.50 ±0.20	≥35	≤44	≥22	≤28
FITCOTUBE® FT-SNV-U(1) 40/20	40.0	0.70 ±0.20	20.0	1.50 ±0.20	≥40	≤47	≥26	≤30
<b>2.5:1</b>								
FITCOTUBE® FT-SNV-U(1) 10/4	10.0	0.70 ±0.20	4.0	1.60 ±0.20	≥8	≤12.5	≥5	≤8
FITCOTUBE® FT-SNV-U(1) 12/5	12.0	0.70 ±0.20	5.0	1.60 ±0.20	≥10	≤15.5	≥6.5	≤10
FITCOTUBE® FT-SNV-U(1) 15/6	15.0	0.70 ±0.20	6.0	1.60 ±0.20	≥12	≤18.5	≥7.5	≤12
FITCOTUBE® FT-SNV-U(1) 20/8	20.0	0.70 ±0.20	8.0	1.60 ±0.20	≥16	≤25	≥10	≤16
FITCOTUBE® FT-SNV-U(1) 25/10	25.0	0.70 ±0.20	10.0	1.70 ±0.20	≥19	≤31	≥12	≤20
FITCOTUBE® FT-SNV-U(1) 30/10	30.0	0.70 ±0.20	12.0	1.80 ±0.20	≥24	≤37.5	≥15	≤24
FITCOTUBE® FT-SNV-U(1) 35/14	35.0	0.70 ±0.20	14.0	1.80 ±0.20	≥26	≤44	≥17	≤28
<b>3:1</b>								
FITCOTUBE® FT-SNV-U(1) 15/5	15.0	0.70 ±0.20	5.0	1.80 ±0.20	≥10	≤18	≥6	≤11.5
FITCOTUBE® FT-SNV-U(1) 20/7.5	20.0	0.70 ±0.20	7.5	1.80 ±0.20	≥14.5	≤23.5	≥9	≤15
FITCOTUBE® FT-SNV-U(1) 25/8.5	25.0	0.70 ±0.20	8.5	2.00 ±0.20	≥16	≤30	≥10	≤18.8
FITCOTUBE® FT-SNV-U(1) 30/10	30.0	0.70 ±0.20	10.0	2.10 ±0.20	≥19	≤35	≥12	≤22.5
FITCOTUBE® FT-SNV-U(1) 40/13	40.0	0.70 ±0.20	13.0	2.10 ±0.20	≥24	≤47	≥15	≤30

Special sizes on request

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · [www.gremco.de](http://www.gremco.de) •

PSD No.: 20230605113019

Version: UWM0623-0

Print Date: 05. Jun. 2023

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Flexible flame retardant polyolefin heat shrink tubing

## FITCOTUBE® FT-SNV-U(1)

Properties	Unit	Requirement
Thermal		
Concentricity before shrink	%	≥65
Concentricity after shrink	%	≥85
Longitudinal change	%	-5 ~ +5
Flammability	--	Burning time less than 30S. The indicator flag / bottom cotton is not ignited
Low temperature flexibility (-55°C±2°C/4h±10min)	--	No cracking
Resistant to rupture after being heated (158°C±2°C/168h±2h)	--	No cracking
Heat Shock (180°C±2°C/4h±10min)	--	No cracking, dripping or flowing
Crack resistance after heating (120°C±2°C/168h±2h)	--	Cut extension length ≤ 5mm
Load deformation (125°C±2°C/60min±5min)	%	≤50
Temperature change	--	No cracking
Mechanical		
Tensile strength	MPa	≥10.4
Ultimate elongation	%	≥300
After Heat Aging (158°C±2°C/168h±2h) Tensile Strength	MPa	≥7.3
Ultimate Elongation	%	≥100
Shore hardness	--	≤A/15: 95
Electrical		
Volume resistance	Ω.cm	≥1.0×10 <sup>12</sup>
Breakdown voltage -Room temperature -After Aging (158°C±2°C/168h±2h)	V	≥7000 ≥3500
Chemical		
Water absorption (23°C±2°C/24h±1h)	%	≤0.5
Copper corrosion (158°C±2°C/168h±2h)	--	No corrosion

Also available with adhesive liner on request.