

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT500SW

FT500SW is a cross-linked, flexible and flame-retardant polyolefin heat shrink tubing suitable for a wide range of applications. Particularly suited for electrical cable insulation and anticorrosion protection.

Operating temperature: -55°C to +125°C

Min full shrink temp.: +125°C

Shrink ratio: 2 : 1

Standard color: Black, Red, Blue, Green, Yellow, White, Yellow/Green, other colors on request



Description	As supplied (mm)	After shrinkage (mm)	
		I.D.	W.T.
FT500SW-0.8	1.1±0.2	0.50	0.22
FT500SW-1.0	1.5±0.2	0.65	0.28
FT500SW-1.5	2.0±0.2	0.85	0.32
FT500SW-2.0	2.5±0.2	1.00	0.35
FT500SW-2.5	3.0±0.2	1.30	0.38
FT500SW-3.0	3.5±0.2	1.50	0.40
FT500SW-3.5	4.0±0.2	1.80	0.42
FT500SW-4.0	4.5±0.2	2.00	0.45
FT500SW-4.5	5.0±0.2	2.30	0.50
FT500SW-5.0	5.5±0.2	2.50	0.55
FT500SW-6.0	6.5±0.2	3.00	0.55
FT500SW-8.0	8.5±0.3	4.00	0.60
FT500SW-10.0	10.5±0.3	5.00	0.60
FT500SW-12.0	12.5±0.3	6.00	0.60
FT500SW-14.0	14.5±0.3	7.00	0.65
FT500SW-16.0	16.5±0.4	8.00	0.70
FT500SW-18.0	19.0±0.5	9.00	0.80
FT500SW-20.0	21.0±0.5	10.00	0.80
FT500SW-22.0	23.0±0.5	11.00	0.80
FT500SW-25.0	26.0±0.5	12.50	0.90
FT500SW-28.0	29.0±0.5	14.00	0.90
FT500SW-30.0	31.5±1.0	15.00	0.95
FT500SW-40.0	41.5±1.0	20.00	0.95
FT500SW-50.0	≥50.0	25.00	1.00
FT500SW-60.0	≥60.0	31.00	1.00
FT500SW-80.0	≥80.0	41.00	1.20
FT500SW-90.0	≥90.0	46.00	1.20
FT500SW-100.0	≥100.0	51.00	1.20
FT500SW-120.0	≥120.0	61.00	1.30
FT500SW-150.0	≥150.0	76.00	1.30

*further dimensions on request

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · www.gremco.de •

PDS No.: 20230621153408

Version: UWM0623-1

Print Date: 19. Apr. 2024

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT500SW

Attributes	Test Method	Typical Value
Mechanical		
Tensile strength	ASTM D 2671	≥10.4MPa
Ultimate Elongation	ASTM D 2671	≥200%
Longitudinal change	ASTM D2671	-5% to ~+5%
After ageing (158°C x 168h): Tensile strength Ultimate elongation		≥7.3MPa ≥100%
Flammability	ASTM D 2671 (method C)	VW-1
Electrical		
Dielectric strength (KV/mm)	ASTM D 149	≥15
Volume resistivity	ASTM D 876	≥1x10 ¹⁴ Ω x cm
Voltage withstand (2500V / 60s)	UL224	No breakdown

Packaging: On spools.

Storage requirements: Avoid direct sunlight, rain and trampling.
 Temperature: -10°C to 45°C.
 Humidity: annual mean ≤75%, less than 30 days > 75%, ≤95% one year.
 Max storage period : 36 months from the date of production