

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT555-AG

FITCOTUBE® FT555-AG is made of cross-linked polyolefin, with zig-zag inner air groove to guide the air flow and prevent bulging or wrinkling caused by trapped air after shrinkage on curved rubber hoses. Its excellent abrasion resistance offers high protection of the automobile pipelines and extends their service life.

Operating temperature:	-40°C to +125°C
Min. full shrink temperature:	+125° C
Shrink ratio:	3:1 & 2:1
Standard color:	Black Other colors on request



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after shrinkage (max.)	after shrinkage (nom.)**
FT555-AG 18/8	18	8	1.1 ±0.2
FT555-AG 21/7.8	21	7.8	1.1 ±0.2
FT555-AG 27/10	27	10	1.1 ±0.2
FT555-AG 39/14	39	14	1.2 ±0.2
FT555-AG 51/21	51	21	1.3 ±0.2
FT555-AG 60/22	60	22	1.3 ±0.2
FT555-AG 76/38	76	38	1.5 ±0.2
FT555-AG 100/35	100	35	1.5 ±0.2

**Wall thickness will be less if tubing recovery is restricted during shrinkage

Special sizes on request

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT555-AG

Packaging: On spools, cut lengths on request.

Properties	Test Method	Typical Value
Mechanical		
Tensile strength	ASTM D 2671	≥ 14MPa
Ultimate elongation	ASTM D 2671	≥ 350%
Specific density	ASTM D 2671	1.05g/cm ³ ~ 1.15g/cm ³
Abrasion resistance	TL 52668 C	≥144,000
Resistance against dynamic loads	TL 52668 C	Pass
Thermal		
Low temperature flexibility (4h x -40°C)	ASTM D 2671	No cracking
Heat shock (4h x 225°C)	ASTM D 2671	No cracking, no dripping, no flowing
Heat ageing (168h/158°C) Tensile strength Ultimate elongation	ASTM D 2671	≥ 10MPa ≥ 280%
Thermal stability (-35°C to 120°C)	TL 52668 C	Pass
Flammability	FMVSS 302	Pass
Chemical		
Water absorption (24h x 23°C)	ASTM D 2671	≤ 0.5%
Resistance to chemicals (24h / 23°C) - coolant - engine oil - engine cleaner - gasoline - diesel - road salt	TL 52668 C	Pass

Key Benefits:

- Abrasion resistance polyolefin material
- Heat shrink tube with inner air groove
- Smooth shrink, air-tight seal when bent
- Halogen free
- Will meet the requirements of TL52668

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · www.gremco.de •

PDS No.: 2022111111249

Version: UWM1122-6

Print Date: 26. Jun. 2024

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.