

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT700

Cross-linked, halogen-free, non-meltable Polyolefin heat-shrink tube. Protection of electrical and mechanical devices in commercial applications, where smooth surfaces are required.

Operating temperature: - 55°C to +105°C, short time up to + 200°C

Shrink temperature: + 115° C / Shrinking starts at 90°C

Shrink ratio: 2: 1

Standard colors: Black, other colors on request.



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after full recovery (max.)	after full recovery (nom.)
FT700-120	1,20	0,60	0,40
FT700-160	1,60	0,80	0,43
FT700-240	2,40	1,20	0,51
FT700-320	3,20	1,60	0,51
FT700-480	4,80	2,40	0,51
FT700-640	6,40	3,20	0,64
FT700-950	9,50	4,80	0,64
FT700-1270	12,70	6,40	0,64
FT700-1900	19,10	9,50	0,76
FT700-2540	25,40	12,70	0,89
FT700-3100	31,80	15,90	0,89
FT700-3800	38,10	19,10	1,02
FT700-5100	50,80	25,40	1,14
FT700-7600	76,20	38,10	1,18

Packaging: On spools. Cut or printed lengths on request.
Special sizes on request.

Processing note: Care for clean and accurate cutting edge. Start shrinkage on the end.
Pre-heat metal body.

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · www.gremco.de •

PDS No.: 20250214152734

Version: UWM0225-0

14 February 2025

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT700

Attributes	Testing	Requirements	Value
Mechanical			
Tensile Strength	ASTM D 638	Min. 10,4 MPa	19.2 MPa
Elongation at Break	ASTM D 638	Min. 200%	≥ 440%
Longitudinal Change	JIS C 2133	-5% ± 10%	- 5 %
Specific. Gravity	ASTM D 792	-	0,92
Hardness (shore D)			42
Electrical			
Volume Resistivity	ASTM D 876	Min. $10^{16} \Omega \cdot \text{cm}$	$1.6 \times 10^{16} \Omega \cdot \text{cm}$
Dielectric Strength	UL224	2.5kV AC * 60s	Passed
Chemical			
Water Absorption (23°C / 24h)	ASTM D 570	-	0,09%