

Fluoropolymer heat-shrink tubing

FITCOTUBE® FT230

Highly flexible, solvent-resistant fluoropolymer-heat shrink tube. For applications that require a high temperature resistance or chemical resistance and also require a low shrinkage temperature.

Operating temperature: - 55°C to + 230°C (black sleeves only)

Shrink temperature: + 130°

Shrink ratio: 2 : 1

Standard colors: Black



Standard dimensions:

Description	Inner diameter (mm)		Wall thickness (mm)	
	as supplied (min.)	after full recovery (max.)	after full recovery (nom.)	after full recovery thin-walled model*
FT230	3.20	1.60	0.65 – 0.95	0.23 – 0.31
FT230	4.80	2.40	0.75 – 1.05	0.23 – 0.31
FT230	6.40	3.20	0.72 – 1.08	0.28 – 0.38
FT230	9.50	4.80	0.72 – 1.08	0.28 – 0.38
FT230	12.70	6.40	0.72 – 1.08	0.28 – 0.38
FT230	19.10	9.50	0.90 – 1.30	0.36 – 0.50
FT230	25.40	12.70	0.92 -1.48	0.41 – 0.55

*if you would like to order a thin-walled model, please mention **FT230(TW)**.

Packaging: On Spools.
Special sizes on request.
Cut and printed lengths on request.

Processing note: Care for clean and accurate cutting edge.
Start shrinkage on the end.
Pre-heat metal body.

Fluoropolymer heat-shrink tubing

FITCOTUBE® FT230

Attributes	Testing	Value
Physical		
Tensile strength	SAE-AMS-DTL-23053	≥ 14 MPa
Ultimate Elongation	SAE-AMS-DTL-23053	≥ 400 %
Longitudinal Change	SAE-AMS-DTL-23053	- 5 %
Water absorption (23°C x 24h)	SAE-AMS-DTL-23053	pass (max 0.1 %)
Elongation after heat ageing (250°C x 168h)	SAE-AMS-DTL-23053	≥ 300 %
Low tempriture flexibility (-55°C x 4h)	SAE-AMS-DTL-23053	pass
Copper Corrosion (175°C x 16h)	SAE-AMS-DTL-23053	pass
Electrical		
Volume resistivity	SAE-AMS-DTL-23053	≥ 10 ¹⁴ Ω/cm
Dielectric strength	SAE-AMS-DTL-23053	15 kV/mm
Chemical		
Flammability	UL 224	pass
Water absorption (23°C x 24h)	SAE-AMS-DTL-23053	pass
Liquid resistance (24°C x 24h)	SAE-AMS-DTL-23053	pass
Vacuum emission	NASA SP-R-0022	pass